



NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D3 mm
Magnetized direction	Through 3 mm direction
Weight	0.11 g/pc
Br	12.2 KGs
Coercive-Force Hcb	≥ 11.3 KOe
Intrinsic Coercive Force Hcj	≥ 12 KOe
(BH) Max	36 MGOe
Working Temperature	$\leq 80^{\circ}\text{C}$

宁波贝威机电有限公司
NINGBO BESTWAY M&E CO., LTD

吕新民



NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com(Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D5 mm
Magnetized direction	Through 5 mm direction
Weight	0.50 g/pc
Br	12.2 KGs
Coercive-Force Hcb	≥ 11.3 KOe
Intrinsic Coercive Force Hcj	≥ 12 KOe
(BH) Max	36 MGOe
Working Temperature	$\leq 80^{\circ}\text{C}$





NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D8 mm
Magnetized direction	Through 8 mm direction
Weight	2.04 g/pc
Br	12.2 KGs
Coercive-Force Hcb	≥ 11.3 KOe
Intrinsic Coercive Force Hcj	≥ 12 KOe
(BH) Max	36 MGOe
Working Temperature	$\leq 80^{\circ}\text{C}$





NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D10 mm
Magnetized direction	Through 10 mm direction
Weight	3.97 g/pc
Br	12.2 KGs
Coercive-Force Hcb	≥ 11.3 KOe
Intrinsic Coercive Force Hcj	≥ 12 KOe
(BH) Max	36 MGOe
Working Temperature	$\leq 80^{\circ}\text{C}$

