



# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*5*2 mm
Magnetized direction	Through 2 mm direction
Weight	1.9 g/pc
Pull Force	1.3 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤ 80°C

宁波贝威机电有限公司  
NINGBO BESTWAY M&E CO., LTD

吕新民



# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*10*2 mm
Magnetized direction	Through 2 mm direction
Weight	3.8 g/pc
Pull Force	1.9 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





## NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

### Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*10*5 mm
Magnetized direction	Through 5 mm direction
Weight	9.5 g/pc
Pull Force	4.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*10*10 mm
Magnetized direction	Through 10 mm direction
Weight	19 g/pc
Pull Force	9.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*15*2 mm
Magnetized direction	Through 2 mm direction
Weight	5.7 g/pc
Pull Force	2.3 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





## NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

### Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*15*5 mm
Magnetized direction	Through 5 mm direction
Weight	14.25 g/pc
Pull Force	5.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*15*10 mm
Magnetized direction	Through 10 mm direction
Weight	28.5 g/pc
Pull Force	11.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





# NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

## Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L25*15*15 mm
Magnetized direction	Through 15 mm direction
Weight	42.75 g/pc
Pull Force	17 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C







## NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

### Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L50*10*5 mm
Magnetized direction	Through 5 mm direction
Weight	19 g/pc
Pull Force	6.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





## NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

### Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L50*10*10 mm
Magnetized direction	Through 10 mm direction
Weight	38 g/pc
Pull Force	13.5 KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C





## NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

### Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	L80*10*5 mm
Magnetized direction	Through 5 mm direction
Weight	30.4 g/pc
Pull Force	8.5 kg±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤80°C

